




INSTALLATION, OPERATION, & MAINTENANCE GUIDE

PVC BALL VALVES

Threaded & Solvent Connections, Schedule 80, 150 WOG



MODELS

T-701

S-701



IMPORTANT

For safe and proper operation, please read the enclosed installation, operation, and maintenance instructions prior to using any Jomar Valve product. Save this document for reference.

Only qualified personnel should undertake the procedures outlined in this document. Jomar Valve, its agents, representatives, and employees assume no liability for the use of these procedures. These procedures are offered as suggestions only.

Note that failure to follow the enclosed instructions may damage the product and/or void any applicable warranties.



PVC Ball Valves

PVC, Threaded & Solvent Connections, Schedule 80, 150 WOG

Models: T-701, S-701



Threaded Connection



Solvent Connection

UNION CONNECTION - SOLVENT

Solvent cementing of socket end connections to pipe should be performed per ASTM specifications D2855-87. Cut pipe square. Chamfer and de-burr pipe. Surfaces must be cleaned and free of dirt, moisture, oil and other foreign material. Apply primer to inside socket surface of end connector. Never allow primer or cement to contact valve ball or end connector O-Ring sealing surfaces, as leaking may result. Use a scrubbing motion. Repeat applications may be necessary to soften the surface of the socket. Next, liberally apply primer to the male end of the pipe to the length of the socket depth. Again apply to the socket, and without delay, apply cement to the pipe while the surface is still wet with primer. Next apply cement lightly, but uniformly to the inside of the socket. Apply a second coat of cement to the pipe, and assemble the end connector to the pipe, rotating the end connector quarter-turn in one direction as it is slipped to full depth on to the pipe. The end connector should be held in position for approx. 30 seconds to allow the connection to “set”. After assembly, wipe off excess cement. Full set time is a minimum of 30 minutes at 60° to 100°F. Full cure time should be based on the chart below.


Joint Cure Schedule

The cure schedules are suggested as guides. They are based on laboratory test data, and should not be taken to be the recommendations of all cement manufacturers. Individual manufacturer’s recommendations for their particular cement should be followed.


Temperature Range during cure period	1/2"-1-1/4" Test Pressures		1-1/2"- 3" Test Pressures		4"-5" Test Pressures		6"-8" Test Pressures	
	180 psi	180-370 psi	180 psi	180-315 psi	180 psi	180-315 psi	180 psi	180-315 psi
60°-100°F	1h	6h	2h	12h	6h	18h	8h	24h
40°-60°F	2h	12h	4h	24h	12h	36h	16h	48h
20°-40°F	6h	36h	12h	72h	36h	4 days	3 days	9 days
10°-20°F	8h	48h	16h	96h	72h	8 days	4 days	12 days
<10°F	Extreme care should be exercised on all joints made where pipe, fittings, or cement is below 10°F							

A. It is important to note that at temperatures colder than 20°F on sizes that exceed 3", test results indicate that many variables exist in the actual cure rate of the joint. The data expressed in these categories represent estimated averages. In some cases, cure will be achieved in less time, but isolated test results indicate that even longer periods of cure may be required.

B. These cure schedules are based on laboratory test data obtained on Net Fit Joints (NET FIT=in a dry fit the pipe bottoms snugly in the fitting socket without meeting interference).



Threaded Connection



Solvent Connection

MATERIALS - THREADED & SOLVENT CONNECTION

No.	Part	Material
1	Body	UPVC
2	Ball / Stem	UPVC
3	Seat (2)	EPDM
4	O-Ring	EPDM
5	Handle	ABS Plastic
6	Bolt	Steel - Zinc Plated
7	Cap	ABS Plastic

UNION CONNECTION - THREADED

Wrap threads of pipe with Teflon tape of 3 to 3-1/2 mil thickness. The tape should be wrapped in a clockwise direction starting at the first or second full thread. Overlap each wrap by 1/2 the width of the tape. The wrap should be applied with sufficient tension to allow the threads of a single wrapped area to show through without cutting the tape. The wrap should continue for the full effective length of the thread. Pipe sizes 2" and greater will not benefit with more than a second wrap, due to the greater thread depth. To provide a leak proof joint, the pipe should be threaded into the end connection “hand tight”. Using a strap wrench only (never use a stillson type wrench), tighten the joint an additional 1/2 to 1-1/2 turns past hand tight. Tightening beyond this point may induce excessive stress that could cause failure.

OPERATION

These are quarter-turn ball valves, and are bidirectional. When the handle is perpendicular to the valve body, it is in the closed position. These valves should be operated in fully open/closed positions. Allowing the valve to operate in a partially-open position will cause wear on the seats.



WARNING:

PLEASE READ THE FOLLOWING INFORMATION PRIOR TO INSTALLING AND USING (PVC/CPVC) JOMAR VALVES, STRAINERS, FILTERS, AND OTHER ASSOCIATED PRODUCTS. FAILURE TO FOLLOW THESE INSTRUCTIONS MAY RESULT IN SERIOUS INJURY.

1. Jomar Valve guarantees its products against defective material and workmanship only. Jomar Valve assumes no responsibility for damage or injuries resulting from improper installation, misapplication, or abuse of any product.
2. Jomar Valve assumes no responsibility for damage or injury resulting from chemical incompatibility between its products and the process fluids to which they are subjected. Customer should always test to determine application suitability.
3. The maximum recommended fluid velocity through any Jomar Valve PVC/CPVC product is eight feet per second. Higher flow rates can result in possible damage due to the water hammer effect. Also note that maximum operating pressure is dependent upon material selection as well as operating temperature.
4. Jomar Valve products are designed primarily for use with non-compressible liquids. They should **NEVER** be used or tested with compressible fluids such as compressed air or nitrogen.
5. Systems should always be depressurized and drained prior to installing or maintaining Jomar Valve PVC/CPVC products.
6. Temperature effect on piping systems should always be considered when the systems are initially designed. Piping systems must be designed and supported to prevent excess mechanical loading on Jomar Valve equipment due to system misalignment, weight, shock, vibration, and the effects of thermal expansion and contraction.
7. Because of PVC and CPVC plastic products become brittle below 40°F, Jomar Valve recommends caution in their installation and use below this temperature.
8. Operating torque is affected by many factors including fluid chemistry, viscosity, flow rate and temperature. These should be considered when sizing electric or pneumatic actuator.
9. Due to differential thermal expansion rates between metal and plastic, transmittal of pipe vibration, and pipe loading forces **DIRECT INSTALLATION OF METAL PIPE INTO PLASTIC CONNECTIONS IS NOT RECOMMENDED**. Wherever installation of plastic valve into metal piping system is necessary, it is recommended that at least 10 pipe diameters in length of plastic pipe be installed upstream and downstream of the plastic valve to compensate for the factors mentioned above.